## Product Data Sheet



Product identification **H 4 GT** Article number 30100002

**Product group** high duty flat belt

**Function** power transmission, transportation

flat belt transmission, transportation belt, printing machines, mail sorting **Application** 

machines, paper stacker

logistics, cardboard, packaging, power generation, bookbindery, paper Industry

processing

**Product construction** 

Material friction cover Characteristics friction cover

Color friction cover Thickness friction cover

Material traction layer

Material reverse cover Characteristics reverse cover

Color reverse cover Thickness reverse cover elastomer

rough structured

green 0.6 mm

polyamide

polyamide fabric fabric structure

black uncoated

**Product characteristics** 

Total thickness

Belt weight

Standard production width

Maximum tensile force

-at 1% elongation

Minimum pulley diameter

Operating temperatures

Permanently antistatic DIN EN 20284

Flammability DIN EN 20340

Chemical resistance

1.3 mm (± 0.2 mm)

1.3 kg/m<sup>2</sup>

500 mm

140 N/mm

4 N/mm

25 mm

yes

Min: -20 °C

oil and grease resistant

Max:

80 °C

176 °F

**Endless joining** 

Recommended joining

Joining length

wedge joining

30 mm

Joining material

Polyamide glue

Rubber glue

Additional material

Note

Glue F

Allow adhesive to evaporate for approx. 5 min after application. Hot bonding can be used after 24 h.

Joining parameters

Pressing temperatures

Pressing time

120 °C 15 min

248 °F

pressure plate fabric

helt

silicone paper heating plate

Alternative joining methods

Finger joining Step joining

Mechanical joining

no nο

G001

through continuous development. Since the VIS GmbH has no influence on the specific conditions of use, there can be differences in the data and information. Therefor, no liability can be accepted for the qualification of the product for the specific application.



03/18

- specifications subject to change without notice -

The listed performance data, information on application and use are only recommendations and were identified under normal conditions and are subject to the changes

