Product Data Sheet



Product identification	H 15 LT	Article number	er 30100015	
Product group	high duty flat bel	t		
Function	power transmissi	power transmission		
Application	flat belt transmiss lathes	flat belt transmission, saw mill drives, mill drive, water turbines, mills and lathes		
Industry	power generatior	n, wood industry		
Product construction				
Material friction cover	leather			
Characteristics friction cover	grinded			
Color friction cover Thickness friction cover	grey 2.0 mm			
	2.0 mm			
Material traction layer	polyamide			
Material reverse cover	polyamide fabric			
Characteristics reverse cover	fabric structure			
Color reverse cover	black			
Thickness reverse cover	uncoated			
Product characteristics				
Total thickness	3.8 mm (± 0.3 m	m)		
Belt weight	3.8 kg/m ²			
Standard production width Maximum tensile force	500 mm 660 N/mm			
-at 1% elongation	15 N/mm			
Minimum pulley diameter	200 mm			
Operating temperatures	Min: -20 °C	-4 °F Max: 80 °C	176 °F	
Permanently antistatic DIN EN 20284	yes			
Flammability DIN EN 20340 Chemical resistance	no oil and grease re	cistont		
Chemical resistance	on and grease re	SIStant		
Endless joining				
Recommended joining Joining length	wedge joining 100 mm			
<u> </u>	100 mm		x	
Joining material				
Polyamide glue Rubber glue	Glue F	Contraction of the second		
Additional material	1C solution			
		n to the leather before the Glue	e F and dry. Then apply	
Note		to evaporate for approx. 5 mi		
Joining parameters			pressure plate	
Pressing temperatures	120 °C	248 °F	silicone paper	
Pressing time	60 min		belt	
Alternative joining methods			silicone paper	
Finger joining	no		heating plate	
Step joining	no			
Mechanical joining	A3			

The listed performance data, information on application and use are only recommendations and were identified under normal conditions and are subject to the changes through continuous development. Since the VIS GmbH has no influence on the specific conditions of use, there can be differences in the data and information. Therefor, no liability can be accepted for the qualification of the product for the specific application.

