Product Data Sheet



Product identification	H 5 LL	Artic	cle number	30100018		
Product group	high duty flat b	pelt				
Function	power transmi	power transmission				
Application	flat belt transn lathes	nission, saw mill drive	es, mill drive, w	ater turbines, mills a	and	
Industry	power generat	tion, wood industry				
Product construction						
Material friction cover	leather					
Characteristics friction cover	grinded					
Color friction cover Thickness friction cover	grey					
Thickness fiction cover	1.2 mm					
Material traction layer	polyamide					
Material reverse cover	leather					
Characteristics reverse cover	grinded					
Color reverse cover	grey					
Thickness reverse cover	1.2 mm					
Product characteristics						
Total thickness	3.1 mm (± 0.4	mm)				
Belt weight	3.1 kg/m ²					
Standard production width	500 mm					
Maximum tensile force -at 1% elongation	220 N/mm 5 N/mm					
Minimum pulley diameter	40 mm					
Operating temperatures	Min: -20 °	C -4 °F Max:	80 °C 17	6 °F		
Permanently antistatic DIN EN 20284	4 yes					
Flammability DIN EN 20340	no sil sud susses					
Chemical resistance	oil and grease	resistant				
Endless joining						
Recommended joining Joining length	wedge joining 75 mm					
	75 1111					
Joining material						
Polyamide glue	Glue F					
Rubber glue Additional material						
Additional material	1C solution	tion to the leather bef	fore the Glue F	and dry. Then apply	v	
Note		ow to evaporate for a			Ŷ	
Joining parameters		33355		pressure	e plate	
Pressing temperatures	120 °C	248 °F		silicone p		
Pressing time	40 min				belt	
Alternative joining methods				silicone p	paner	
Finger joining	no			heating		
Step joining	no					
Mechanical joining	A2					

The listed performance data, information on application and use are only recommendations and were identified under normal conditions and are subject to the changes through continuous development. Since the VIS GmbH has no influence on the specific conditions of use, there can be differences in the data and information. Therefor, no liability can be accepted for the qualification of the product for the specific application.

