## Product Data Sheet



Product identification M 5 TT HC Article number 30200003

**Product group** machine tape

**Function** power transmission, transportation

flat belt transmission, transportation, printing machines, distributing **Application** 

systems, sorters

logistics, packaging, power generation, printing industry, paper Industry

processing

**Product construction** 

Material friction cover polyamide fabric Characteristics friction cover fabric structure Color friction cover black

Thickness friction cover uncoated

Material traction layer polyamide

Material reverse cover polyamide fabric Characteristics reverse cover fabric structure

Color reverse cover black Thickness reverse cover uncoated

**Product characteristics** 

Operating temperatures

Total thickness 1.2 mm (± 0.2 mm)

Belt weight 1.2 kg/m<sup>2</sup> Standard production width 500 mm Maximum tensile force 220 N/mm

-at 1% elongation 5 N/mm Minimum pulley diameter 30 mm

Permanently antistatic DIN EN 20284

Flammability DIN EN 20340

Chemical resistance oil and grease resistant

Min:

yes

**Endless joining** 

Recommended joining wedge joining Joining length 30 mm

Joining material

Polyamide glue Glue F Rubber glue Additional material

Allow adhesive to evaporate for approx. 5 min after application. Hot Note bonding can be used after 24 h.

-20 °C

Max:

80 °C

176 °F

Joining parameters

Pressing time

120 °C

25 min

Alternative joining methods

Pressing temperatures


Finger joining no Step joining nο Mechanical joining G001

pressure plate silicone paper

helt

silicone paper heating plate

The listed performance data, information on application and use are only recommendations and were identified under normal conditions and are subject to the changes through continuous development. Since the VIS GmbH has no influence on the specific conditions of use, there can be differences in the data and information. Therefor, no liability can be accepted for the qualification of the product for the specific application.



248 °F



03/18

