

Product identification

F 12/2 EQ U08GST / U0

Article number 20200026

Product group

food conveyor belt

Mode of transport

all-round belt for sloping and horizontal running

Application

transport of unit load, transition belts

Industry

packaging industry, potato and fish industry, metal manufacturing, car industry

Belt construction

Material conveying side	polyurethane (PU)
Characteristics conveying side	rough structure (GST), not adhesive
Color conveying side	petrol
Cover thickness conveying side	0.8 mm
Shore hardness A°	A 93 (± 3)
Material traction layer	polyester fabric
Number of fabrics	2
Material running side	polyester fabric
Characteristics running side	slippery
Color running side	colourless
Cover thickness running side	impregnated

Product characteristics

Total thickness	3.1 mm (± 0.10 mm)
Belt weight	2.7 kg/m ²
Standard production width	2,000 mm
Maximum tensile force	160 N/mm
- at 1% elongation (DIN EN ISO 527-1)	12 N/mm
Minimum pulley diameter	60 mm
Minimum pulley diameter backflexing	90 mm
Knife edge suitable	no
Operation temperatures	Min: -20 °C -4 °F Max: 100 °C 212 °F
Permanently antistatic (DIN EN ISO 21178)	yes
Flammability (DIN EN ISO 340)	no
Chemical resistance	oil and grease resistant (see list of resistance)
Complies with FDA	yes (see declaration of conformity)
Meets EU regulation for food contact	yes (see declaration of conformity)

Installation terms

Slider bed suitable	yes
Carrying rollers suitable	yes
Low noise application	no
Accumulation mode	no
Inclined transportation	yes
Buckling conveyor	yes
Curved installation	no
Friction coeff. on slider bed of steel	0.15
Friction coeff. on slider bed with friction cover	0.3
Troughed installation	no
Cross rigidity	yes, extra transverse stable

The listed performance data, information on application and use are only recommendations and were identified under normal conditions and are subject to the changes through continuous development. Since the VIS GmbH has no influence on the specific conditions of use, there can be differences in the data and information. Therefore, no liability can be accepted for the qualification of the product for the specific application.